



DURATERMIC SHADOW



<u>PROPERTIES</u>	<u>VALUE</u>	<u>UNITS</u>	<u>STANDARD</u>
Thickness	200	μ	ISO 4591
<u>MECHANICAL PROPERTIES</u>			
Tensile strength at break			
M.D.	23	MPa	EN ISO 527
T.D.	22	MPa	EN ISO 527
Elongation at break			
M.D.	500	%	EN ISO 527
T.D.	600	%	EN ISO 527
Dart-test F50			
FLAT	550	gr	ISO 7765
FOLD	300	gr	ISO 7765
<u>OPTICAL PROPERTIES</u>			
Global light transmission	75	%	EN 2155
Thermicity	87	%	EN 13206
Diffuse light transmission	70	%	EN 2155
<u>AGEING PROPERTIES</u>			
Agricultural seasons	2	Years (*)	
<u>SPECIAL PROPERTIES</u>			
25% Shadow			

(*) Duration in areas with radiation of 150 kly / year. For different conditions, contact SOLPLAST, S.A.



All the data contained in this Specification Sheet has been obtained through our own experience and is offered at an informative level. They are obtained under optimal process conditions and therefore may vary depending on product dimensions, extruding equipment, etc. SOLPLAST reserves the right to change these data at any time without notice. These data are given with all the goodwill but as the circumstances and conditions upon which this information could be used are beyond our control, we cannot accept any responsibility for any lost or damage caused by its use.

For any other option consult with us in the email info@solplast.com